

Removal of Heavy Metal Nickel-Ions from Wastewaters Using Carbon Nanodots from Frying Oil

by Sulhadi 36

Submission date: 02-Aug-2022 08:54AM (UTC+0700)

Submission ID: 1877918564

File name: 2017_Procedia_170_Dika_Removal_of_heavy_metal.pdf (818.89K)

Word count: 2139

Character count: 11742



Engineering Physics International Conference, EPIC 2016

3
Removal of Heavy Metal Nickel-Ions from Wastewaters Using Carbon
Nanodots from Frying Oil

Mahardika Prasetya Aji*, Pradita Ajeng Wiguna, Jotti Karunawan, Annisa Lidia Wati,
and Sulhadi

1
Department of Physics, Universitas Negeri Semarang, Semarang, Indonesia

Abstract

3
Heavy metals pollution becomes a serious environmental problem 2 cause heavy metals are non biodegradable and some heavy metal ion such as nickel is known as toxic metal. In this study, we investigated the natural sorb 2 materials for removing heavy metals nickel-ions in the wastewaters using carbon nanodots (C-Dots) from frying oil. C-Dots was re 2 tted from frying oil by the hydrothermal method at temperature 300°C for 2 2. The results showed that C-Dots could remove heavy metal nickel-ions in the solution. Electric current from the solution of heavy metal nickel-ion decreases with the number of C-D 1 and time that used in the process of removal. The intensity of adsorption spectra fr 7 nickel ions contained in the wavelength 600-800 nm. C-Dots from frying oil have a great potential as a natural sorbent.

© 2017 Published by Elsevier Ltd. This is an open access article under the CC BY-NC-ND license
9 <http://creativecommons.org/licenses/by-nc-nd/4.0/>.

Peer-review under responsibility of the organizing committee of the Engineering Physics International Conference 2016

Keywords: carbon nanodots; frying oil; nickel; wastewater; adsorption; electrical current

1. Introduction

The presence of heavy metal ions such as cadmium, cobalt, copper, nickel, chromium and lead in water that exceeds the threshold becoming a serious problem for the environment. Commonly, the properties of heavy metals are non biodegradable and toxic that can cause various negative impact on living organisms [1]. Water pollution due 5 heavy metals can be caused from many different of human activities such as mining and industrial waste [2]. Widely various techniques have been used for removal of heavy metal ions from water such as precipitation, ion exchange, membrane filtration and adsorption [3,4]. Recently, many reports shows on the development to remove the heavy metal in the water with a consideration about low cost and effective impact, such as adsorption technique [5,6]. Various materials that have strong adsorption to remove any contaminants in the water, including heavy metal is from class of carbon materials such as activated carbon, carbon nanotubes and graphene oxide [5-7]. Activated carbon has a wide surface area, whereas the carbon nanotubes and graphene oxide becomes material much studied in environmental applications include water purification due to the presence of function group is dominated by carboxyl and hydroxyl that forms graphitic structure. So it is very effective as an adsorbent materials because have strong interaction to cations through electrostatics mechanism [8].

Recent a new class material from carbon is carbon nanodots (C-Dots). It could be produced from the polymerization process with a simple hydrothermal method at low temperatures. Structure C-Dots contain of ox 1 n atoms that are abundant in the arrangement of function group carboxyl and hydroxyl which obtained from precursors form of carbon sources such as citric acid, soy milk, orange juice, ginger, food waste, waste paper and frying oil [9-15]. Different from the carbon which usually black and has a weak fluorescence, C-Dots have properties such as strong fluorescence, non-toxic and insoluble in water. So that makes this materials have a high attractiveness to be assessed and used 1 various application fields such as bioimaging, photocatalyst and sensor [16]. In this work, we report a preliminary study for the use of C-Dots from frying oil for a new function to remove heavy metal nickel ions. The amount of C-Dots and time process is varied to investigate for derive the optimum condition to remove a heavy metal ions. The performance of the C-Dots from frying oil to remove a heavy metal nickel ions are estimated from electrical current and adsorption spectra.

2. Experiment

2.1. Materials

Used frying oil (Bimoli were obtained from Salim Ivomas Pratama Tbk. Indonesia) as precursor for the synthesise C-Dots. Meanwhile, C-Dots were obtained by heating them at temperature $T = 300^{\circ}\text{C}$ for 2h and the properties of C-Dots were observed previously [15]. Heavy metal ions were obtained by dissolved nickel nitrate $\text{Ni}(\text{NO}_3)_2$ purchased from Merck-Germany.

2.2. Batch adsorption studies of C-Dots

Removal heavy metal nickel ion from wastewates use batch method with C-Dots from frying oil as adsorbent materials. Batch adsorption experiment were performed in a magnetic stirrer at 32°C using a 250 ml Beaker glass containing 100 ml solution of nickel 20 ppm and use various volume of C-Dots 5 ml, 10 ml, 15 ml, 20 ml, 25 ml and 30 ml. Then, the experiment set for various time process of 10 min, 20 min, 30 min, 40 min, 50 min and 60 min. The solution of heavy metal and C-Dots have different densities so easily separated after the removal process.

2.3. Characterization

A solution of heavy metal removal process results were analyzed from electrical and optical properties. Due to the solution of heavy metal is electrolyte, so performance of removal process were estimated by electrical current that can be streamed. Scheme of electrical current measurements was shown in Fig 1. In addition, the other analysis was supported by measurements of the absorption spectra of heavy metal solution use UV-Vis-NIR Ocean Optics type USB 4000.




Fig. 1. Schematic illustration of electrical current on heavy metal solution.

3. Results and Discussion

3.1. Electrical current of heavy metal solution

The results of electrical current measurements from heavy metal solution was shown in Fig 2. Electrical current that measured was decreases with the amount of volume C-Dots and time process. Electrical current is decreased shows that the electrolyte properties of heavy metal nickel-ions solution is reduced. It indicates that the amount of heavy metal-nickel ion is reduced due to adsorption process by the particles of C-Dots. The simple results show that C-Dots of frying oil could remove heavy metal nickel-ions.




Fig. 2. Electrical current of heavy metal solution with various : (a). volume of C-Dots and (b). time process removal

The process of removal heavy metal nickel-ions occurs through the adsorption mechanism by electrostatic interaction between particle of C-Dots and nickel-ions. The surface of C-Dots has a negative charged (Zeta potential -28mV at pH 7) that derived from carboxyl and hydroxyl groups function [17]. This adsorption mechanism is similar with the interaction between C-Dots and cancer cells. The negative charge on the surface of C-Dots have an electrostatic interaction in the solution as shown in Fig. 3. Increasingly the amount of C-Dots and time process causes nickel-ions which bond is increase. The electrical current of heavy metal decreased that shows a simply phenomenon of removal nickel-ions with C-Dots from frying oil. Additional analysis is required to describe the heavy metal removal process. In this study, the measurement of absorption spectra from UV-Vis-NIR devices are used to analyze the process of removal because generally heavy metal-ions have a responds to the wavelength range of UV [18].




Fig. 3. Schematic illustration of adsorption mechanism with various: (a). volume of C-Dots and (b). time process

3.2. Adsorption spectrum of heavy metal nickel solution

The result of measurement from adsorption spectrum of heavy metal nickel solution was shown in Fig. 4. Heavy metal nickel solution has absorption spectrum in the wavelength range of 600-800 nm [18]. The absorption spectra appears in a solution of heavy metal nickel without C-Dots, 5 ml C-Dots, 10 ml C-Dots and 15 C-Dots. The intensity of absorption spectrum decreases until the same as absorption spectrum of water with increasing the amount of C-Dots are used in the removal process. In addition, the absorption spectrum of heavy metal solution with various time process are decreased too. The results of absorption spectrum measurement of heavy metal nickel solution corresponds to the results of electrical current. Thus, C-Dots of frying oil capable to remove heavy metal nickel-ion.




Fig. 4. Adsorption spectrum of heavy metal nickel ions with various : (a) volume of C-Dots and (b) time process

4. Conclusion

In this preliminary study, for the first time, C-Dots from frying oil could remove heavy metal nickel-ions. The removal process of nickel-ions is strongly influenced by the amount of C-Dots and time process. Electrical and optical properties from the solution of heavy metal ions decreases with increasing the amount of C-Dots and the time process. Furthermore, C-Dots from frying oil have a great potential as a sorbent materials.

References

- [1] F. Fu and Q. Wang, Removal of heavy metal ions from wastewaters: A review, *Journal of Environmental Management*, 92 (2011) 407-418
- [2] M. Visa and A. M. Chelaru, Hydrothermally modified fly ash for heavy metals and dyes removal in advanced wastewater treatment, *Applied Surface Science*, 303 (2014) 14-22
- [3] Z. Ding, X. Hu, V. L. Morales, and B. Gao, Filtration and transport of heavy metals in graphene oxide enabled sand columns, *Chemical Engineering Journal*, 257 (2014) 248-252
- [4] Y. Zhou, B. Gao, A. R. Zimmerman, J. Fang, Y. Sun, and X. Cao, Sorption of heavy metals on chitosan-modified biochar sand its biological effects, *Chemical Engineering Journal*, 231 (2013) 512-518
- [5] M. Kobya, E. Demirbas, E. Senturk, and M. Ince, Adsorption of heavy metal ions from aqueous solutions by activated carbon prepared from apricot stone, *Bioresource Technology*, 96 (2005) 1518-1521
- [6] A. Gopalakrishnan, R. Krishnan, S. Thangavel, G. Venugopal, and S. J. Kim, Removal of heavy metal ions from pharma-effluents using graphene-oxide nanosorbents and study of their adsorption kinetics, *Journal of Industrial and Engineering Chemistry*, 30 (2015) 14-19
- [7] M. Yusuf, F. M. Elfighi, S. A. Zaidi, E. C. Abdullah, and M. A. Khan, Applications of graphene and its derivatives as an adsorbent for heavy metals and dyes removal: A systematic and comprehensive overview, *RSC Advances*, 5 (2015) 50392-50420
- [8] Z. Ding, X. Hu, V. L. Morales, and B. Gao, Filtration and transport of heavy metals in graphene oxide enabled sand columns, *Chemical Engineering Journal*, 257 (2014) 248-252
- [9] M. L. Bhasare, A. Talib, M. S. Khan, S. Pandey, and H. F. Wu, Synthesis of fluorescent carbon dots via microwave carbonization of citric acid in presence of tetraoctylammonium ion, and their application to cellular bioimaging, *Springer*, 182 (13) (2015) 2173-2181
- [10] C. Zhu, J. Zhai, and S. Dong, Bifunctional fluorescent carbon nanodots: green synthesis via soy milk and application as metal-free electrocatalysts for oxygen reduction, *Chemical Communications*, 48 (2012) pp. 9367-9369
- [11] S. Sahu, B. Behera, T. K. Maiti, and S. Mohapatra, Simple one-step synthesis of highly luminescent carbon dots from orange juice: Application as excellent bio-imaging agents, *Chemical Communications*, 48 (70) (2012) 8835-8837.
- [12] C. L. Li, C. M. Ou, C. C. Huang, W. C. Wu, Y. P. Chen, T. E. Lin, L. C. Ho, C. W. Wang, C. C. Shih, H. C. Zhou, Y. C. Lee, W. F. Tzeng, T. J. Chiou, S. T. Chu, J. Cang, and H. T. Chang, Carbon dots prepared from ginger exhibiting efficient inhibition of human hepatocellular carcinoma cells, *Journal of Materials Chemistry B*, 2 (2014) 4564-4571
- [13] J. Wang, Y. Hwee Ng, Y. F. Lim, and G. W. Ho, Vegetable-extracted carbon dots and their nanocomposites for enhanced photocatalytic H₂ production, *RSC Advances*, 4 (2014) 44117-44123
- [14] J. Wei, X. Zhang, Y. Sheng, J. Shen, P. Huang, S. Guo, J. Pan, B. Liu and B. Feng, Simple one-step synthesis of water-soluble fluorescent carbon dots from waste paper, *New Journal Chemistry*, 38 (2014) 906-909
- [15] M. P. Aji, P. A. Wiguna, Susanto, R. Wicaksono, and Sulhadi, Identification of carbon dots in waste cooking oil, *Advanced Materials Research*, 1123 (2015) 402-405.
- [16] M. P. Aji, P. A. Wiguna, S. A. Sucinngtyas, Susanto, N. Rosita, and Sulhadi, Carbon nanodots from frying oil as catalyst for photocatalytic degradation of methylene blue assisted solar light irradiation, *American Journal of Applied Sciences*, 13 (4) (2016) 432-438
- [17] M. Havrdova, K. Hala, J. Skopalik, K. Tomankova, M. Petr, K. Cepe, K. Polakova, J. Tucek, A. B. Bourlino, and R. Zboril, Toxicity of carbon dots: Effect of surface functionalization on the cell viability, reactive oxygen species generation and cell cycle, *Carbon*, 99 (2016) 238-248
- [18] N. E. Wezynfeld, W. Goch, W. Bal, and T. Fraczyk, *cis*-Urocanic acid as a potential nickel(II) binding molecule in the human skin, *Dalton Transactions*, 43 (2014) 3196-3201

Removal of Heavy Metal Nickel-Ions from Wastewaters Using Carbon Nanodots from Frying Oil

ORIGINALITY REPORT

22%

SIMILARITY INDEX

11%

INTERNET SOURCES

14%

PUBLICATIONS

10%

STUDENT PAPERS

PRIMARY SOURCES

- 1 Mahardika Prasetya Aji, Pradita Ajeng Wiguna, Siti Aisyah Suciningtyas, Susanto, Nita Rosita, Sulhadi. "Carbon Nanodots from Frying Oil as Catalyst for Photocatalytic Degradation of Methylene Blue Assisted Solar Light Irradiation", American Journal of Applied Sciences, 2016
Publication 5%
- 2 Submitted to October University for Modern Sciences and Arts (MSA)
Student Paper 4%
- 3 www.semanticscholar.org
Internet Source 3%
- 4 www.researchgate.net
Internet Source 3%
- 5 pubs.rsc.org
Internet Source 2%
- 6 M. Fukue, T. Inoue, Y. Fujimori, K. Tanabe, K. Kita, T. Chida, A. Nishihara. "Resistivity change during transport of heavy metal in sand", Engineering Geology, 2006
Publication 1%

7

dspace.vutbr.cz

Internet Source

1 %

8

autodocbox.com

Internet Source

1 %

9

www.coursehero.com

Internet Source

1 %

Exclude quotes On

Exclude matches < 15 words

Exclude bibliography On