

## HASIL UJI KEMIRIPAN TURNITIN

No. : 776/CTN/VI/2024

UPT Perpustakaan Unnes menerangkan bahwa artikel yang berjudul  
Preparation, Characterization, and Release Study of Nanosilica/Chitosan Composite  
Films

Nama Penulis : Nadya Alfa Cahaya Imani, S.T., M.Eng.

Email : [nadya.alfa@mail.unnes.ac.id](mailto:nadya.alfa@mail.unnes.ac.id)

NIM/NIP/NIK/NIDN : 199207282019032025

Nomor HP : 081327142734

Skor Hasil Kemiripan : 11%

Asal Fakultas/Unit : FT

Asal Universitas/Instansi : Universitas Negeri Semarang

Surat ini dikeluarkan untuk digunakan dengan sebaik-baiknya.

Semarang, 14 Juni 2024  
Kepala UPT Perpustakaan



Dr. Sungkowo Edy Mulyono, S.Pd., M.Si.  
NIP. 196807042005011001

\*hasil turnitin dapat diunduh melalui akun turnitin masing-masing

# Preparation, Characterization, and Release Study of Nanosilica/Chitosan Composite Films

*by* Nadya Alfa

---

**Submission date:** 14-Jun-2024 09:25AM (UTC+0700)

**Submission ID:** 2402134634

**File name:** ation,\_and\_Release\_Study\_of\_NanosilicaChitosan\_-\_Nadya\_Alfa.docx (362.19K)

**Word count:** 4370

**Character count:** 24400



## Preparation, Characterization, and Release Study of Nanosilica/Chitosan Composite Films

Nadya Alfa Cahaya Imani<sup>1</sup>, Yuni Kusumastuti<sup>2\*</sup>, Himawan Tri Bayu Murti Petrus<sup>2,3</sup>,  
Daniel Timotius<sup>2</sup>, Nur Rofiqoh Eviana Putri<sup>2</sup>, Mime Kobayashi<sup>4</sup>

<sup>1</sup>Department of Chemical Engineering, Faculty of Engineering, Universitas Negeri Semarang, Sekaran Campus, Gunungpati, Semarang, 50229, Indonesia

<sup>2</sup>Department of Chemical Engineering, Faculty of Engineering, Universitas Gadjah Mada, Sleman, Yogyakarta, 55281, Indonesia

<sup>3</sup>Unconventional Geo-resources Research Group, Faculty of Engineering, Universitas Gadjah Mada, Sleman, Yogyakarta, 55281, Indonesia

<sup>4</sup>Division of Biological Science, Nara Institute of Science and Technology, 8916-5 Takayama-cho, Ikoma, Nara 630-0192, Japan

**Abstract.** The development of film materials that can control the release of drugs is needed to create a smart drug delivery system. This paper reports the properties and kinetic studies of film models made of chitosan and nanosilica. Nanosilica was directly incorporated into the chitosan solution to modify and enhance the properties of the composites as potential drug carriers. Fourier transform infrared spectroscopy results acknowledge the successful fabrication of chitosan/nanosilica composite films. Wettability tests showed that the inclusion of nanosilica could make the film more hydrophilic by incorporating up to 5 wt%. The effective diffusion coefficients obtained by mathematical modeling were in the range of  $10^{-6}$  cm<sup>2</sup>/min. Based on the kinetic studies, the power-law model is the most suitable model to explain the mechanism of drug released from composite films with  $k_K$  values ranging from 0.3552 to 0.4279, the value of  $n$  in the range of 0.3103 to 0.3955, and the value of  $R^2$  in the range of 0.9008 to 0.9411. The overall result concludes that these chitosan/nanosilica composite films have great potential to be used as materials for drug carriers.

**Keywords:** Chitosan; Composite Film; Drug delivery system; Kinetic model; Nanosilica

### 1. Introduction

Medicine is an important component of human healthcare as it is a way to provide therapeutic or healing effects for various diseases (Whittam et al., 2016). Conventionally, drugs have been administered to the body through the gastrointestinal tract, rectal injection, or directly into a vein (Batchelor and Marriott, 2013). These methods are inherently less effective because, at each time of administration, a large dose of the drugs has to be given for the drugs to reach the target locations (Wen et al., 2015). Drug administration must be repeated and often cause side effects. Side effects can be allergies or systemic poisoning caused by reactions between the drugs and stomach fluids or the patient's blood. To avoid repeated drug administrations to patients so as to minimize the

8  
\*Corresponding author's email: [yuni\\_kusumastuti@ugm.ac.id](mailto:yuni_kusumastuti@ugm.ac.id), Tel.: +62274555320  
doi: [10.14716/ijtech.v13i2.4733](https://doi.org/10.14716/ijtech.v13i2.4733)

possibility of poisoning caused by excessive drug doses, a drug delivery system that can deliver controlled drug release is needed.

One of the most studied drug delivery systems is the use of a polymer film (thin membrane layer). This form of film has the advantage of being flexible in how it is administered to the body (Chan et al., 2019; Hatanaka et al., 2019). The drug delivery system in the form of films usually uses polymers from natural materials (biopolymers) as the matrix because these materials have biocompatible properties (properties where a material does not cause rejection reactions by the human immune system that detect and attack foreign objects), are biodegradable (the ability of a material to be degraded inside the body), and are nontoxic (Chan et al., 2019; Kalantari et al., 2013; Samadian et al., 2020). One biopolymer that has been gaining attention for this purpose is chitosan. Chitosan is a natural polysaccharide and a derivative of chitin, which can be found in the exoskeleton of shelled animals (crustaceans) (Sedaghat et al., 2017). This compound has antibacterial properties, is nontoxic, and is easy to modify, so it is often chosen to be used for various applications in the fields of food, textiles, waste treatment, agriculture, and health (Revathi and Thambidurai, 2017; Mohamed et al., 2018; Kamdem et al., 2019; Si et al., 2019). Chitosan is also a polymer that has a positive charge (polycation), which makes it good to be used as a matrix for drug delivery systems in the form of a film because it will increase the adhesive properties (ability to stick) of the film (Krisanti et al., 2020; Singh et al., 2020). In its application as a film for drug delivery, like other biopolymers, chitosan has a disadvantage that it is easy to swell; that is, swelling occurs when the film is in a liquid system. This swelling can cause discomfort when the patient uses this film-shaped drug release system. In addition, a high swelling rate will trigger an initial burst release (rapid drug release at the beginning) (Ammar et al., 2009). Therefore, efforts are needed to modify the film from this material to improve its characteristics, especially for applications as a delivery system of drugs or other components.

One way to increase the ability of chitosan film as a drug delivery system is by adding inorganic materials. According to Uragami et al. (2002) and Kusumastuti et al. (2017), the formation of an organic-inorganic film could create a vastly functional materials by combining the film-forming properties of organic polymers and the stability and strength of inorganic compounds. Furthermore, the potential use of organic/inorganic composites as biomaterials in tissue engineering has been reported by Kusumastuti et al. (2018). Also, research conducted by Liu et al. (2019) reported that the addition of an inorganic material, namely nanosilica, can decrease the percentage swelling of the chitosan film and increase the tensile strength of the film. Nanosilica is used because this material has properties such as nontoxic, large drug loading capacity, easy to modify, and biocompatible (Bharti et al., 2015). Another similar study was also conducted by Wu et al. (2019), where mesoporous silica was obtained from tetraethyl orthosilicate and it was added to chitosan for making films, which are able to be applied for food packaging application. The results of the study showed that the prepared hybrid films can slow the release of curcumin and have good antimicrobial activity.

Herein, film as a drug delivery system was prepared by mixing chitosan and nanosilica powder. Curcumin, which is known to have potential as an anticancer drug, was used as a model drug for drug release. Nanosilica addition aimed to modify the structure of the chitosan film so that it can increase resistance to control the speed of drug release. In this study, we report the properties of the films that have been made and investigated their potential as a controlled drug delivery system. Furthermore, we also report mathematical modeling and kinetic studies of drug release from the film. Thus, a simple thin-film model can be obtained and used to foresee the drug release profile of a system for wound dressing.

## 2. Methods

### 2.1. Materials

Chitosan with low-molecular-weight specifications (75–85% degree of deacetylation) and nanosilica (SiO<sub>2</sub>) powder (10–20 nm) were purchased from Sigma Aldrich. Acetic acid glacial (100% w/w) was obtained from Merck, Germany. Phosphate-buffered saline (PBS), pH 7.4, was supplied by the Faculty of Dentistry, Universitas Gadjah Mada, Indonesia.

### 2.2. Chitosan–Nanosilica Solution Preparation

Low-molecular-weight chitosan was dissolved in a 1% (v/v) acetic acid water solution to make a 1% (w/v) chitosan solution. The mixture was stirred in a closed container at room temperature for 3 h. A certain amount of nanosilica powder (PC: film with 0% by weight of nanosilica/weight of chitosan; CSD25: film with 2.5% weight of nanosilica/weight of chitosan; CSD50: film with 5% weight of nanosilica/weight of chitosan; CSD75: film with 7.5% weight of nanosilica/weight of chitosan; CSD100: film with 10% weight of nanosilica/weight of chitosan) was mixed in the solutions and stirred at room temperature for 4 h (Imani, 2018).

### 2.3. Drug Loading

Curcumin, according to the concentration calculation (20% weight of curcumin/weight of chitosan), was stirred in Tween 80 (70% by weight of Tween 80/weight of chitosan). The solution was stirred at room temperature until it became homogeneous. The film matrix solution was poured to the curcumin/Tween 80 solution and stirred again for 3 h in a closed container. The solution was then poured into a 11-cm-diameter polyethylene (PE) petri dish with a volume of 5 mL/petri dish and dried for 48 h at 30°C (Timotius et al., 2020).

### 2.4. Film Characterization

The procured samples were characterized using Fourier transform infrared (FTIR) spectroscopy (Shimadzu IR Prestige-21) in the wavenumber ranged between 4000–400 cm<sup>-1</sup>. Changes in functional groups were observed by comparing the spectra of prepared films with those of pure components. Surface area and pore diameter and intensity analyses were carried out using a surface area analyzer instrument (NOVA series, Quantachrome).

### 2.5. Drug Release Test

Prepared films were cut using a 1.25-cm-diameter punch. They were immersed in 20 mL of PBS solution. Periodically, the sample solution was taken using a pipette and was analyzed using a spectrophotometer (Genesys-20) at a wavelength (λ<sub>max</sub>) of 421 nm for absorbance measurement (Hazra et al., 2015). Each analyzed solution was returned to the original solution so that the total volume of the sample solutions remained the same.

### 2.6. Kinetic Study

The diffusion process in drug release was modeled using the mathematical equation and conditions proposed by Timotius et al. (2020), as shown in Equation 1:

$$\frac{\partial^2 C}{\partial x^2} = \frac{1}{D_{ef}} \frac{\partial C}{\partial t} \quad (1)$$

In addition to the mathematical modeling that has been compiled, four mathematical models are also used to represent the mechanism of drug released from the film matrix, namely zero order (Equation 2), first order (Equation 3), Higuchi (Equation 4), and Korsmeyer Peppas or often called the power-law model (Equation 5) (Dash et al., 2010).

$$C_t = C_0 + k_z t \quad (2)$$

$$C_t = C_0 e^{-k_f t} \quad (3)$$

$$\frac{C_t}{C_\infty} = k_H t^{1/2} \quad (4)$$

$$\frac{C_t}{C_\infty} = k_K t^n \quad (5)$$


where  $C_t$  is the cumulative concentration of the drug released at time  $t$ ,  $C_0$  is the initial amount of the drug,  $C_\infty$  is the amount of drug at the equilibrium state, and  $k$  is constant for the kinetic model ( $k_z$ , zero order;  $k_f$ , first order;  $k_H$ , Higuchi;  $k_K$ , power law).

## 3. Results and Discussion

### 3.1. FTIR Characterization Analysis

The existence of interactions between materials in the film was analyzed by FTIR spectroscopy. The spectra produced from chitosan, nanochitosan, curcumin, and chitosan/silica films that have been loaded with curcumin are shown in Figure 1. Changes in the peaks in the obtained FTIR spectra were observed. Chitosan used has a distinctive vibration from its functional groups, namely a large vibration area at 3100–3600  $\text{cm}^{-1}$ , which imply the existence of O–H and/or N–H bonds; a peak at 2877  $\text{cm}^{-1}$ , which suggest the presence of C–H alkyl bonds; a peak at 1651  $\text{cm}^{-1}$ , which represents C=O stretch and N–H deformation in primary amine groups; and a peak at 1558  $\text{cm}^{-1}$ , signaling the presence of C–N stretching and N–H deformation in secondary amine groups (Liu et al., 2019).

In nanosilica, Si–O–Si is linear, which is shown by the presence of stretching vibrations in the area at 1080–1200  $\text{cm}^{-1}$ , Si–OH is shown with a peak at 964  $\text{cm}^{-1}$ , and Si–O is shown by the existence of a peak at 474  $\text{cm}^{-1}$ . The addition of nanosilica to the film matrix causes changes in the resulting film spectra. The shifts from 1651 and 1558  $\text{cm}^{-1}$  to 1629 and 1563  $\text{cm}^{-1}$  indicate a possible interaction in the form of hydrogen bond formation between the hydroxyl groups of the nanosilica and the amine groups present in chitosan. Meanwhile, the change of a peak at 1090  $\text{cm}^{-1}$  to a large area vibration from 1500 to 1180  $\text{cm}^{-1}$  may be due to the arrangement of the –Si–O–C bond produced by the reaction between the silanol groups of nanosilica and the carbonyl groups in chitosan and Si–O–Si stretching. In addition, a peak at 474  $\text{cm}^{-1}$  also appeared, which indicates the presence of Si–O bonds in the chitosan/nanosilica film. Furthermore, from the results of FTIR characterization on curcumin, typical vibrations of curcumin can be seen as a peak at 1512  $\text{cm}^{-1}$ , which indicates the presence of C=O bonds, and there is also C–O enol, which is indicated by a peak at 1280  $\text{cm}^{-1}$ . In the spectrum of prepared film, peaks at 1512 and 1280  $\text{cm}^{-1}$  were observed, thus confirming the presence of curcumin in the hybrid film.



**Figure 1** FTIR spectra for chitosan (C), nanosilica (NS), curcumin (Cur), and prepared film (CSD50)

### 3.2. Surface Observation


Brunauer-Emmett-Teller (BET) surface area analysis was carried out to compare the surface area of a film made of chitosan alone and a chitosan/nanosilica hybrid film. The addition of nanosilica has an impact on increasing the surface area of the film (Table 1). The surface area of a film made of chitosan alone (PC) was  $6.12 \text{ m}^2/\text{g}$  while that of CSD50 was  $8.522 \text{ m}^2/\text{g}$ , with a 23.0% increase. At the same time, the average pore size of the film decreased from  $40.7$  to  $35.95 \text{ \AA}$  with the addition of nanosilica. The results indicate that the addition of nanosilica creates a film that has more pores but in small sizes. Changes in the pore structure of the film will affect the film's properties such as mechanical strength and permeability. The decrease in pore size increases the tensile strength of a film and slows diffusion of the retained liquid due to the barrier effect (Fahim et al., 2015a, 2015b).

**Table 1** Summary of surface area analysis

Sample	Total surface area ( $\text{m}^2/\text{g}$ )	Pore size ( $\text{\AA}$ )
PC	6.93	40.7
CSD50	8.522	35.95

### 3.3. Wettability

The effect of blending nanosilica on the hydrophobic/hydrophilic properties of the chitosan films was assessed by measuring the contact angles between water droplets and the surface of the films. Smaller angles mean that the films have hydrophilic properties, and greater angles mean reduced hydrophilic properties, or it can be called more hydrophobic (Dwivedi et al., 2017). The results of the water contact angle (WCA) measurements are presented in Figure 2. From the bar chart in the figure, it can be said that the addition of nanosilica in an amount of 5% by weight of nanosilica/weight of chitosan (CSD50) increases the WCA value of the film from  $65.2 \pm 1.4^\circ$  to  $93.05 \pm 0.35^\circ$ .




**Figure 2** WCAs of the prepared films

The statistical analysis using analysis of variance (ANOVA) showed less than 0.05 in probability value for each individual sample. The presence of silica in the film showed a significant difference. However, increasing the amount of silica further to 7.5% (CSD75) or 10% (CSD100) by weight of nanosilica/weight of chitosan resulted in smaller WCA values ( $55.55 \pm 1.25^\circ$  or  $50.1 \pm 0.6^\circ$ , respectively) when compared with PC (0% nanosilica). Basically, silica, including the one in nanosized scale, should be hydrophilic due to the presence of an OH group in the silanol group. In CSD25 and CSD50, the presence of the group is decreased as a result of interaction with chitosan. However, in CSD75 and CSD100, the excessive amount of silica makes it difficult for the solution to be homogeneous. The nanosilica tends to form aggregates with similar molecules. The aggregate formation will

cause an increase in the number of –OH groups, leading to more hydrophilic properties (Rallini and Kenny, 2017).

### 3.4. Drug Release Profiles and Kinetic Studies

Using curcumin as a model, drug release tests were performed to confirm the effectiveness of the prepared films in holding the drug and controlling drug release rates. All films made of chitosan and nanosilica mixture showed slower drug release compared with a film made of chitosan alone (Figure 3). The results show a profile where the drug will be gradually released over time, and for a certain period, the release will be sustained at constant rates. The profile is influenced by several factors, namely by components of the drug carrier matrix, pH of the solution, and temperature (Barleany et al., 2020). Statistical analyses using ANOVA showed a significant difference in the mixing variable of the amount of nanosilica in the film matrix on the cumulative amount of drug released.




**Figure 3** Release profile of drug from films

**Table 2** Value of diffusion parameter

Sample	$D_{ef}$	$H_A$
PC	$1.031 \times 10^{-5}$	$6.1767 \times 10^3$
CSD25	$9.9372 \times 10^{-6}$	$6.1456 \times 10^3$
CSD50	$4.1935 \times 10^{-6}$	$6.1102 \times 10^3$
CSD75	$7.7981 \times 10^{-6}$	$6.1525 \times 10^3$
CSD100	$8.0042 \times 10^{-6}$	$6.1398 \times 10^3$

The data for the effective diffusion value of each prepared film are shown in Table 2. The effective diffusivity coefficient values for all films containing nanosilica are lower than those of the films without the addition of nanosilica (PC). This decrease is possibly because the addition of nanosilica made the structure of the film tighter, thus giving it more resistance and making it more difficult for the drug in the middle area of the film to be released. However, the optimal decrease occurred only in CSD50; the effective diffusion value at the addition of a higher amount of nanosilica, namely in CSD75 and CSD100, started to increase again, but still smaller than that of PC. This is possibly because the nanosilica tends to form aggregates with similar molecules and the excessive amount of nanosilica in the film makes the matrix solution not homogeneous so that there is a gap in the film obtained and the drug can come out faster.





**Figure 4** Linear fitting of drug release using the (a) zero-order model, (b) first-order model, (c) Higuchi model, and (d) power-law model

In addition to fitting mathematical models that have been compiled, the drug release results were also compared with several known release kinetic models, namely the zero-order, first-order, Higuchi, and power-law models. Data and calculation results using each model are shown in Figure 4 and Table 3. Based on the figures and the  $R^2$  data, the drug release trend of the samples produced in this study is the closest to the power-law model. The  $R^2$  value shown in comparison with the power-law linear model ranges from 0.9008 to 0.9411, where the CSD50 has the highest number. The power ( $n$ ) values reported for all films are less than 0.5. The  $n$  value in this power law illustrates the mechanism of drug release from the film. If  $n < 0.5$ , then the release mechanism involves Fickian diffusion, which means that solvent diffusion is much more dominant than the polymer chain relaxation process in the film matrix (Bruschi, 2015).

**Table 3** Parameter for kinetics of release models

Sample	Zero order		First order		Higuchi		Power law		
	$k_z$	$R^2$	$k_f$	$R^2$	$k_H$	$R^2$	$k_K$	$n$	$R^2$
PC	0.2114	0.5101	0.4921	0.8736	0.3977	0.7462	0.4503	0.4525	0.8551
CSD25	0.0191	0.5001	0.2926	0.7362	0.3601	0.7376	0.4279	0.3955	0.9008
CSD50	0.0138	0.6253	0.0469	0.7335	0.2605	0.8446	0.3552	0.3103	0.9411
CSD75	0.0164	0.5750	0.1199	0.7484	0.3092	0.8079	0.3935	0.3533	0.9159
CSD100	0.0168	0.5241	0.1406	0.6947	0.3174	0.7619	0.3995	0.3602	0.9091

#### 4. Conclusions

Composite films made of nanosilica and chitosan have been successfully prepared by varying the ratio of the amount of nanosilica to chitosan. The addition of nanosilica to the film matrix up to 5% by weight of nanosilica/weight of chitosan increased the hydrophobic properties of the film. However, higher nanosilica content led to smaller WCA values or more hydrophilic films. Performance tests on drug release show that all films containing a mixture of nanosilica have higher drug-retaining ability than films made only with chitosan. The calculation results show that the effective diffusion values of chitosan/nanosilica films are in the range of  $4.1935 \times 10^{-6}$  to  $9.9372 \times 10^{-6}$  cm<sup>2</sup>/min and the most suitable drug release mechanism follows the power-law model with  $R^2$  value ranging from 0.9008 to 0.9411. From the results, it can be stated that chitosan and nanosilica composites have great potential to be used as materials for drug carriers. However, further study of the optimal methods and conditions for film formation is needed to make this controlled drug delivery system even more effective.

#### Acknowledgements

The authors appreciate and acknowledge the partial financial support provided by the Global Collaboration Program of the Nara Institute of Science and Technology (FY2016-2018) sponsored by MEXT, Japan.

#### References

- Ammar, H.O., Ghorab, M., Kamel, R., 2009. Polymeric Matrix System for Prolonged Delivery of Tramadol Hydrochloride, Part I : Physicochemical Evaluation. *AAPS Pharmaceutical Science and Technology*, Volume 10(1), pp. 7–20. doi: 10.1208/s12249-008-9167-0
- Barleany, D.R., Ananta, C.V., Maulina, F., Rochmat, A., Alwan, H., Erizal, 2020. Controlled Release of Metformin Hydrogen Chloride from Stimuli-Responsive Hydrogel Based on Poly(N-Isopropylacrylamide)/Chitosan/Polyvinyl Alcohol Composite. *International Journal of Technology*, Volume 11, pp. 511–521. doi: 10.14716/ijtech.v11i3.2330
- Batchelor, H.K., Marriott, J.F., 2013. Formulations for Children: Problems and Solutions. *British Journal of Clinical Pharmacology*, Volume 79(3), pp. 405–418. doi: 10.1111/bcp.12268
- Bharti, C., Gulati, N., Nagaich, U., Pal, A., 2015. Mesoporous Silica Nanoparticles in Target Drug Delivery System: A Review. *International Journal of Pharmaceutical Investigation*, Volume 5(3), pp. 124–133. doi: 10.4103/2230-973X.160844
- Bruschi, M.L., 2015. *Mathematical Models of Drug Release*. Elsevier, United Kingdom. doi: 10.1016/B978-0-08-100092-2.09993-8
- Chan, S.Y., Goh, C.F., Lau, J.Y., Tiew, Y.C., Balakrishnan, T., 2019. Rice Starch Thin Films as a Potential Buccal Delivery System: Effect of Plasticiser and Drug Loading on Drug Release Profile. *International Journal of Pharmaceutics*, Volume 562, pp. 203–211. doi: 10.1016/j.ijpharm.2019.03.044
- Dash, S., Murthy, P.N., Nath, L., Chowdhury, P., 2010. Kinetic Modeling on Drug Release from Controlled Drug Delivery Systems. *Acta Poloniae Pharmaceutica*, Volume 67(3), pp. 217–223
- Dwivedi, C., Pandey, I., Pandey, H., Ramteke, P.W., Pandey, A.C., Mishra, S.B., Patil, S., 2017. Electrospun Nanofibrous Scaffold as a Potential Carrier of Antimicrobial Therapeutics for Diabetic Wound Healing and Tissue Regeneration. In: *Nano- and Microscale Drug Delivery Systems*, Grumezescu, A.M., (ed.), Elsevier, United Kingdom, pp. 147–164. doi: 10.1016/B978-0-323-52727-9.00009-1

- Fahim, I.S., Mamdouh, W., Salem, H.G., 2015a. Chitosan Nanocomposite Mesoporous Membranes: Mechanical and Barrier Properties as a Function of Temperature. *Journal of Materials Science Research*, Volume 4(4). doi: 10.5539/jmsr.v4n4p1
- Fahim, I.S., Marei, N., Salem, H.G., Mamdouh, W., 2015b. Effect of Graphene and Fullerene Nanofillers on Controlling the Pore Size and Physicochemical Properties of Chitosan Nanocomposite Mesoporous Membranes. *Journal of Nanomaterials*, Volume 2015. doi: 10.1155/2015/979561
- Hatanaka, T., Saito, T., Fukushima, T., Todo, H., Sugibayashi, K., Umehara, S., Takeuchi, T., Okamura, Y., 2019. Potential of Biocompatible Polymeric Ultra-Thin Films, Nanosheets, as Topical and Transdermal Drug Delivery Devices. *International Journal of Pharmaceutics*, Volume 565, pp. 41–49. doi: 10.1016/j.ijpharm.2019.04.059
- Hazra, K., Kumar R., Sarkar, B.K., Chowdary, Y.A., Devgan, M., Ramaiah, M., 2015. UV-Visible Spectrophotometric Estimation of Curcumin in Nanoformulation. *International Journal of Pharmacognosy*, Volume 2(3), pp. 127–130. doi: 10.13040/IJPSR.0975-8232
- Imani, N.A.C., 2018. Pengaruh Penambahan Nanosilika terhadap Karakter Fisik Film Kitosan serta Kecepatan Pelepasan Kurkumin. Master's Thesis, Graduate Program, Department of Chemical Engineering, Universitas Gadjah Mada, Yogyakarta, Indonesia
- Kalantari, K., Afifi, A.M., Jahangirian, H., Webster, T.J., 2019. Biomedical Applications of Chitosan Electrospun Nanofibers as a Green Polymer—Review. *Carbohydrate Polymers*, Volume 207, pp. 588–600. doi: 10.1016/j.carbpol.2018.12.011
- Kamdem, D.P., Shen, Z., Nabinejad, O., 2019. Development of Biodegradable Composite Chitosan-Based Films Incorporated with Xylan and Carvacrol for Food Packaging Application. *Food Packaging and Shelf Life*, Volume 21, pp. 100344. doi: 10.1016/j.fpsl.2019.100344
- Krisanti, E.A., Lazuardi, D., Kiresya, K.K., Mulia, K., 2020. Tablet Formulation Containing Chitosan-Alginate Microparticles: Characterization and Release Profile of Xanthones. *International Journal of Technology*, Volume 11(5), pp. 900–909. doi: 10.14716/ijtech.v11i5.4338
- Kusumastuti, Y., Petrus, H.T.B.M., Fiska, Y., 2017. Synthesis and Characterization of Biocomposites Based on Chitosan and Geothermal Silica. *AIP Conference Proceedings*, Volume 1823, pp. 020127. doi: 10.1063/1.4978200
- Kusumastuti, Y., Kobayashi, M., Purwaningtyas, F., Najmina, M., Petrus, H.T.B.M., Putri, N.R.E., Budhijanto, Tanihara, M., 2018. Characterization of Three Dimensional Scaffolds from Local Chitosan/Alginate/Geothermal Silica for Potential Tissue Engineering Applications. *Journal of Engineering Science and Technology*, Volume 13(11), pp. 3500–3515
- Liu, Y., Cai, Z., Sheng, L., Ma, M., Xu, Q., 2019. Influence of Nanosilica on Inner Structure and Performance of Chitosan Based Films. *Carbohydrate Polymers*, Volume 212, pp. 421–429. doi: 10.1016/j.carbpol.2019.02.079
- Mohamed, M.H., Ajaero, C., McMartin, D.W., Peru, K.M., Friesen, V., Simair, M., Headley, J.V., Wilson, L.D., 2018. Solubilized Chitosan Biopolymers for Sequestration of Organic Acids in Aquatic Environments after Biodegradation in a Constructed Wetland Treatment System. *International Journal of Technology*, Volume 9, pp. 1140–1150. doi: 10.14716/ijtech.v9i6.2301
- Rallini, M., Kenny, J.M., 2017. Nanofillers in Polymers. In: *Modification of Polymer Properties*, Elsevier, United Kingdom, pp. 47–86
- Revathi, T., Thambidurai, S., 2017. Synthesis of Chitosan Incorporated Neem Seed Extract (*Azadirachta indica*) for Medical Textiles. *International Journal of Biological Macromolecules*, Volume 104, pp. 1890–1896. doi: 10.1016/j.ijbiomac.2017.02.081

- Samadian, H., Maleki, H., Allahyari, Z., Jaymand, M., 2020. Natural Polymers-Based Light-Induced Hydrogels: Promising Biomaterials for Biomedical Applications. *Coordination Chemistry Reviews*, Volume 420, pp. 213432. doi: 10.1016/j.ccr.2020.213432
- Sedaghat, F., Yousefzadi, M., Toiserkani, H., Najafipour, S., 2017. Bioconversion of Shrimp Waste *Penaeus merguensis* Using Lactic Acid Fermentation: An Alternative Procedure for Chemical Extraction of Chitin and Chitosan. *International Journal of Biological Macromolecules*, Volume 104, pp. 883–888. doi: 10.1016/j.ijbiomac.2017.06.099
- Si, J., Yang, Y., Xing, X., Yang, F., Shan, P., 2019. Controlled Degradable Chitosan/Collagen Composite Scaffolds for Application in Nerve Tissue Regeneration. *Polymer Degradation and Stability*, Volume 166, pp. 73–85. doi: 10.1016/j.polymdegradstab.2019.05.023
- Singh, G., Nayal, A., Malhotra, S., Koul, V., 2020. Dual Functionalized Chitosan Based Composite Hydrogel for Haemostatic Efficacy and Adhesive Property. *Carbohydrate Polymers*, Volume 247, pp. 116757. doi: 10.1016/j.carbpol.2020.116757
- Timotius, D., Kusumastuti, Y., Imani, N.A.C., Rochmadi, Putri, N.R.E., Rahayu, S.S., Wirawan, S.K., Ikawati, M., 2020. Kinetics of Drug Release Profile from Maleic Anhydride-Grafted-Chitosan Film. *Materials Research Express*, Volume 7(4), pp. 046403. doi: 10.1088/2053-1591/ab80d9
- Uragami, T., Okazaki, K., Matsugi, H., Miyata, T., 2002. Structure and Permeation Characteristics of an Aqueous Ethanol Solution of Organic-Inorganic Hybrid Membranes Composed of Poly(Vinyl Alcohol) and Tetraethoxysilane. *Macromolecules*, Volume 35(24), pp. 9156–9163. doi: 10.1021/ma020850u
- Wen, H., Jung, H., Li, X., 2015. Drug Delivery Approaches in Addressing Clinical Pharmacology-Related Issues: Opportunities and Challenges. *AAPS Journal*, Volume 17(6), pp. 1327–1340. doi: 10.1208/s12248-015-9814-9
- Whittam, A.J., Maan, Z.N., Duscher, D., Wong, V.W., Barrera, J.A., Januszyk, M., Gurtner, G.C., 2016. Challenges and Opportunities in Drug Delivery for Wound Healing. *Advances in Wound Care*, Volume 5(2), pp. 79–88. doi: 10.1089/wound.2014.0600
- Wu, C., Zhu, Y., Wu, T., Wang, L., Yuan, Y., Chen, J., Hu, Y., Pang, J., 2019. Enhanced Functional Properties of Biopolymer Film Incorporated with Curcumin-Loaded Mesoporous Silica Nanoparticles for Food Packaging. *Food Chemistry*, Volume 288, pp. 139–145. doi: 10.1016/j.foodchem.2019.03.010

# Preparation, Characterization, and Release Study of Nanosilica/Chitosan Composite Films

## ORIGINALITY REPORT

11%

SIMILARITY INDEX

8%

INTERNET SOURCES

7%

PUBLICATIONS

2%

STUDENT PAPERS

## PRIMARY SOURCES

1	<a href="http://vbn.aau.dk">vbn.aau.dk</a> Internet Source	1%
2	<a href="http://pubs.rsc.org">pubs.rsc.org</a> Internet Source	1%
3	Y Kusumastuti, F Larasati, D R Gunawan, M Najmina, N R E Putri, H T B M Petrus, M Kobayashi. "Comparative Characterization of Chitosan/Gelatin/Geothermal Silica Biocomposites in Two-Dimensional Film and Three-Dimensional Scaffold Forms", IOP Conference Series: Materials Science and Engineering, 2019 Publication	1%
4	Submitted to School of Business and Management ITB Student Paper	1%
5	<a href="http://studentsrepo.um.edu.my">studentsrepo.um.edu.my</a> Internet Source	1%

6

Bingren Tian, Jianhua Cheng, Tianping Zhang, Yumei Liu, Dejun Chen. "Multifunctional chitosan-based film loaded with hops  $\beta$ -acids: Preparation, characterization, controlled release and antibacterial mechanism", Food Hydrocolloids, 2021

Publication

1 %

7

Hakan Çiftçi, Muhammet Davut Arpa, İsmail Musab Gülaçar, Levent Özcan, Bahri Ersoy. "Development and evaluation of mesoporous montmorillonite/magnetite nanocomposites loaded with 5-Fluorouracil", Microporous and Mesoporous Materials, 2020

Publication

1 %

8

[repository.untar.ac.id](https://repository.untar.ac.id)

Internet Source

1 %

9

[www2.mdpi.com](http://www2.mdpi.com)

Internet Source

1 %

10

[westminsterresearch.westminster.ac.uk](https://westminsterresearch.westminster.ac.uk)

Internet Source

1 %

11

Du, W.L.. "Preparation, characterization and adsorption properties of chitosan nanoparticles for eosin Y as a model anionic dye", Journal of Hazardous Materials, 20080501

Publication

&lt;1 %

[etd.uwc.ac.za](https://etd.uwc.ac.za)

12	Internet Source	<1 %
13	<a href="http://lib.unnes.ac.id">lib.unnes.ac.id</a> Internet Source	<1 %
14	<a href="http://ntnuopen.ntnu.no">ntnuopen.ntnu.no</a> Internet Source	<1 %
15	<a href="http://www.scielo.br">www.scielo.br</a> Internet Source	<1 %
16	<a href="http://jddtonline.info">jddtonline.info</a> Internet Source	<1 %
17	<a href="http://www.kmo.org.tr">www.kmo.org.tr</a> Internet Source	<1 %
18	<a href="http://jos.unsoed.ac.id">jos.unsoed.ac.id</a> Internet Source	<1 %

Exclude quotes  On

Exclude bibliography  On

Exclude matches  < 15 words